
PRODUCT SPECIFICATION SHEET

1. PRODUCT NAME

DURUS[®] Asphalt Crack Filler

2. MANUFACTURER

Durus International Corporation
1217 Palolo Avenue
Honolulu, Hawaii 96816-2525
TEL: (808) 733-8682
FAX: (808) 737-1808
EMAIL: info@durusinternational.com
WEBSITE: www.durusinternational.com

3. PRODUCT DESCRIPTION

Basic Use: DURUS[®] Asphalt Crack Filler is a tough, trowel grade patch material designed to fill cracks and holes up to ½" wide on asphalt pavements. It has a rough sand texture when applied and dries to a hard, durable finish. DURUS[®] Asphalt Crack Filler is formulated to work with all other DURUS[®] Asphalt sealing products.

Composition and Materials: DURUS[®] Asphalt Crack Filler is a black acrylic polymer and aggregate mixture that comes ready-to-use, in convenient size pails.

Limitations: Do not apply DURUS[®] Asphalt Crack Filler over wet pavement or where water vapor is being transmitted through the surface. Substrate temperature should be no lower than 60°F (15.5°C) during application; lower temperatures may cause longer drying time.

If rain is anticipated before initial installation, the use of this product should not be permitted. Adequate precautions shall be taken to protect freshly applied DURUS[®] Asphalt Crack Filler from sudden, unexpected rain or other disturbances. DURUS[®] Asphalt Crack Filler should be allowed adequate time to dry completely.

Precautions: Contains acrylic. Avoid contact with eyes and prolonged contact with skin. If material comes in contact with eyes, flush with water repeatedly and contact physician immediately. For further information, see DURUS[®] Asphalt Crack Filler Material Safety Data Sheet (MSDS).

4. INSTALLATION

Surface Preparation: All substrates to be filled must be clean, and free of any dirt, debris or oil contamination. Remove loose materials from crack with a stiff brush or air pressure.

Depending on condition, oil residue and sludge buildup may need to be removed with a DURUS[®] authorized cleaner/degreaser (Formula One) or by microbial remediation (DURUS[®] MC). Follow instructions on label. Rinse cracks thoroughly with water and dry crack completely. Careful use of torch burners may be used to assist crack drying time.

Directions for Use: All surfaces must be completely clean and dry before applying any DURUS[®] Asphalt Crack Filler. Use contents as packaged; do not dilute mixture.

Apply DURUS[®] Primer to surface. Patch primer treated cracks with DURUS[®] Asphalt Crack Filler using a margin trowel. Be sure to work filler into cracks well and up to ½" on both sides of the cracks. Allow material to dry completely (between two and four hours at 85°F [29.4°C]). Talc powder may be sprinkled over DURUS[®] Asphalt Crack Filler to allow light traffic if surface has not completely dried. Clean up is with detergent and water. Apply only when temperature of the surface, the air and this product are above 60°F (15.5°C). Cooler temperatures will cause longer drying times.

5. PACKAGING & COVERAGE

Packaging: DURUS® Asphalt Crack Filler is packaged ready-to-use in a pail containing 25 pounds (11.34 kg.) of material.

Coverage: Each 25 pound (11.34 kg.) unit of DURUS® Asphalt Crack Filler will cover approximately 432 cu. in. (7,079 cu. cm.) by volume. Coverage may vary depending on surface condition and porosity.

6. WARRANTY

Durus International Corporation warrants that DURUS® Asphalt Crack Filler manufactured by it shall be free from material defects. THIS WARRANTY IS GIVEN IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. DURUS INTERNATIONAL CORPORATION MAKES NO WARRANTY AS TO MERCHANTABILITY OR FOR FITNESS OF PURPOSE. Should the DURUS® Asphalt Crack Filler be proven defective, the liability to Durus International Corporation shall be limited to the replacement of the product, F.O.B. Port of Honolulu, Hawaii, United States of America. The replacement of the DURUS® Asphalt Crack Filler shall be the exclusive remedy. Durus International Corporation shall not be liable for any consequential damages. User shall determine the suitability of the product for its intended use and shall assume all risks and liability in connection therewith.

7. MAINTENANCE

DURUS® Asphalt Crack Filler requires no more maintenance than regular blacktop asphalt.

8. TECHNICAL SERVICES

Durus International Corporation personnel are available to provide technical assistance by contacting the Corporate Office or the Manufacturing Plant as listed in Section 2 of this document.

<p>This information is designed to guide the user and has been conscientiously compiled according to the latest state of Durus International Corporation's technology. No liability can be accepted in connection with the use of the product because of the great variety of applications, materials, and working conditions.</p>
--